

BC-517S,BC-517H,BC-517L,BC-517P Mineral Oil Based Liquid Scintillators

Mineral oil based liquid scintillators are used in large tanks where exceptionally long mean free paths are essential and high light output is of secondary importance. These mineral oil scintillators are compatible with acrylic plastics such as Plexiglas® and Perspex®, plus a wide variety of metals and some other plastics and reflective coatings. Glue joints made with solvent action cements should be annealed.

SGCD mineral oil scintillators have flash points rendering them relatively safe for use in large containers and large volume detector arrays. They are especially suited where the expense of large area plastic scintillators would be prohibitive.

SGCD takes special care when manufacturing its mineral oil liquid scintillators. Our people are keenly aware of the particularly high requirements regarding light transmission and product uniformity demanded by the physics community. Therefore, in addition to employing standard, rigorous purification and handling techniques, SGCD uses special test facilities for light transmission measurement in order to guarantee customer satisfaction with every shipment of this scintillator.

Scintillation Properties –

	BC-517S	BC-517H	BC-517L	BC-517P
Light Output, % Anthracene:				
Saturated with Nitrogen	66	52	39	28
Saturated with Air	51	40	30	21
Mean Free Path for 400-500nm light, meters	>4	>5	>5	>6
Wavelength of max. emission, nm	425	425	425	425

Atomic Composition –

No. H Atoms per cc	6.50x10 ²²	7.06x10 ²²	7.40x10 ²²	7.50x10 ²²
No. C Atoms per cc	3.83x10 ²²	3.73x10 ²²	3.68x10 ²²	3.65x10 ²²
Atomic Ratio (H:C)	1.70	1.89	2.01	2.05

General Technical Data –

Refractive Index:	
	BC-517S 1.49
	BC-517H 1.476
	BC-517L 1.471
	BC-517P 1.47
Flash Point (T.O.C.):	
	BC-517S 53°C
	BC-517H 81°C
	BC-517L 102°C
	BC-517P 115°C
Specific Gravity:	
	BC-517S 0.87
	BC-517H 0.86
	BC-517L 0.86
	BC-517P 0.85

Scintillation Products
Organic Scintillators



USA

Saint-Gobain Crystals
17900 Great Lakes Parkway
Hiram, OH 44234
Tel: (440) 834-5600
Fax: (440) 834-8047

Europe

Saint-Gobain Crystals
104 Route de Larchant
BP 521
77794 Nemours Cedex, France
Tel: 33 (1) 64 45 10 10
Fax: 33 (1) 64 45 10 01

P.O. Box 3093
3760 DB Soest
The Netherlands
Tel: 31 35 60 29 700
Fax: 31 35 60 29 214

Japan

Saint-Gobain KK, Crystals Division
3-7, Kojimachi, Chiyoda-ku,
Tokyo 102-0083 Japan
Tel: 81 (0) 3 3263 0559
Fax: 81 (0) 3 5212 2196


China

Saint-Gobain (China) Investment Co., Ltd
15-01 CITIC Building
19 Jianguomenwai Ave.
Beijing 100004 China
Tel: 86 (0) 10 6513 0311
Fax: 86 (0) 10 6512 9843

www.detectors.saint-gobain.com

BC-517S,BC-517H,BC-517L,BC-517P Mineral Oil Based Liquid Scintillators

Emission Spectrum –



Manufacturer reserves the right to alter specifications.
©2005-8 Saint-Gobain Ceramics & Plastics, Inc. All rights reserved.

(08-08)