

BC-521

Gadolinium Loaded Liquid Scintillator

BC-521 is formulated to yield the highest light output possible as well as long term chemical stability. The standard gadolinium concentration is 0.5% by weight, but other concentrations up to 1.5% can be supplied. Since the liquid is normally used in large tanks containing several hundred liters, it employs a high flash point solvent for safety purposes.

The principal applications of BC-521 are for neutron spectrometry and neutrino research. It is ideal for use in large tanks for neutron multiplicity experiments.

Gadolinium has the highest thermal neutron capture cross-section of any element. The neutron capture reaction yields beta particles and several gamma rays having a total energy of about 8 MeV. Delayed coincidence and pulse shape discrimination techniques can be employed.

Scintillation Properties –

Light Output, % Anthracene	68
(for 1% Gd concentration), % Anthracene	57
Wavelength of Maximum Emission, nm	424
Decay Time, short component, ns	3.6
Bulk Light Attenuation, meters	>4

Atomic Composition –


No. of H Atoms per cc	5.25×10^{22}
No. of C Atoms per cc	4.00×10^{22}
Ratio H:C Atoms	1.314
No. of Electrons per cc	2.97×10^{23}

General Technical Data –

Gadolinium Content	0.5%, w/w
Density	0.89g/cc
Refractive Index	1.50
Flash Point	44°C

BC-521 Gadolinium Loaded Liquid Scintillator

Emission Spectrum –



USA

Saint-Gobain Crystals
17900 Great Lakes Parkway
Hiram, OH 44234
Tel: (440) 834-5600
Fax: (440) 834-7680

Europe

Saint-Gobain Crystals
104 Route de Larchant
BP 521
77794 Nemours Cedex, France
Tel: 33 (1) 64 45 10 10
Fax: 33 (1) 64 45 10 01

P.O. Box 3093
3760 DB Soest
The Netherlands
Tel: 31 35 60 29 700
Fax: 31 35 60 29 214

Japan

Saint-Gobain KK, Crystals Division
3-7, Kojimachi, Chiyoda-ku,
Tokyo 102-0083 Japan
Tel: 81 (0) 3 3263 0559
Fax: 81 (0) 3 5212 2196

China

Saint-Gobain (China) Investment Co., Ltd.
15-01 CITIC Building
19 Jianguomenwai Ave.
Beijing 100004 China
Tel: 86 (0) 10 6513 0311
Fax: 86 (0) 10 6512 9843

www.detectors.saint-gobain.com