

# BC-537

## Deuterated Liquid Scintillator

This liquid scintillator is based on specially purified deuterated benzene. It is particularly useful as a neutron detector and in the study of specific interactions such as n + D. BC-537's appreciable pulse shape discrimination properties also make it useful for neutron-gamma discrimination.

BC-537 is encapsulated in Saint-Gobain Crystals & Detectors' range of glass and aluminum cells.

In addition to BC-537, Saint-Gobain Crystals & Detectors supplies deuterated liquid scintillators having higher D:C ratios or higher D:H ratios.

### Scintillation Properties –

Light Output% Anthracene .....	61
Wavelength of maximum emission, nm .....	425
Decay time, principal component, ns .....	2.8

### Atomic Composition –

No. of D Atoms per cc .....	$4.06 \times 10^{22}$
No. of H Atoms per cc .....	$3.55 \times 10^{20}$
No. of C Atoms per cc .....	$4.10 \times 10^{22}$
D:H Ratio .....	114:1
D:C Ratio .....	0.99
No. of electrons per cc .....	$2.87 \times 10^{23}$

### General Technical Data –

Density (20°C) .....	0.954 g/cc
Refractive Index .....	1.50
Flash Point .....	-11°C

Scintillation Products  
Organic Scintillators



#### USA

Saint-Gobain Crystals  
17900 Great Lakes Parkway  
Hiram, OH 44234  
Tel: (440) 834-5600  
Fax: (440) 834-7680

#### Europe

Saint-Gobain Crystals  
104 Route de Larchant  
BP 521  
77794 Nemours Cedex, France  
Tel: 33 (1) 64 45 10 10  
Fax: 33 (1) 64 45 10 01

P.O. Box 3093  
3760 DB Soest  
The Netherlands  
Tel: 31 35 60 29 700  
Fax: 31 35 60 29 214

#### Japan

Saint-Gobain KK, Crystals Division  
3-7, Kojimachi, Chiyoda-ku,  
Tokyo 102-0083 Japan  
Tel: 81 (0) 3 3263 0559  
Fax: 81 (0) 3 5212 2196


#### China

Saint-Gobain (China) Investment Co., Ltd.  
15-01 CITIC Building  
19 Jianguomenwai Ave.  
Beijing 100004 China  
Tel: 86 (0) 10 6513 0311  
Fax: 86 (0) 10 6512 9843

[www.detectors.saint-gobain.com](http://www.detectors.saint-gobain.com)

## BC-537 Deuterated Liquid Scintillator

Emission Spectrum—



Manufacturer reserves the right to alter specifications.  
©2005-8 Saint-Gobain Ceramics & Plastics, Inc. All rights reserved.

(08-08)