

BC-414 Premium Plastic Scintillator

This PVT-based plastic scintillator is formulated for use with wavelength shifter (WLS) bars having short decay times. The traditional green WLS (wavelength shifting) plastics, intended for use with many common blue emitting scintillators, have long decay times – typically ~15ns. To meet the need for scintillator-WLS systems with faster time response, we developed BC-414 and also the WLS plastic BC-484.

While having a relatively short emission spectrum for optical compatibility with BC-484, BC-414 is still sufficiently transparent to its scintillation light to be used in plate sizes up to 50cm (20") on a side. Shorter wavelength scintillators, with emission peaks typically at 375nm, have extremely short light attenuation lengths (<10cm) which limit their useful sizes.

Scintillation Properties –

Light Output, Anthracene	68%
Rise Time, ns	0.7
Decay Constant, main component, ns	1.8
Pulse Width, FWHM, ns	2.7
Wavelength of Maximum Emission, nm	392
Bulk Light Attenuation Length, cm	100

Atomic Composition –

Ratio H:C Atoms	1.10
No. of Electrons per cc ($\times 10^{23}$)	3.37

General Technical Data –

Base	Polyvinyltoluene
Density (g/cc)	1.032 g/cc
Refractive Index	1.58
Expansion Coefficient (per°C, <67°C) ...	7.8×10^{-5}
Softening Point	70°C
Vapor Pressure	May be used in vacuum
Solubility	Soluble in aromatic solvents, chlorinated solvents, acetone, etc. Unaffected by water, dilute acids, lower alcohols, alkalis and pure silicone fluids or grease.

Scintillation Products
Organic Scintillators



USA

Saint-Gobain Crystals
17900 Great Lakes Parkway
Hiram, OH 44234
Tel: (440) 834-5600
Fax: (440) 834-7680

Europe

Saint-Gobain Crystals
104 Route de Larchant
BP 521
77794 Nemours Cedex, France
Tel: 33 (1) 64 45 10 10
Fax: 33 (1) 64 45 10 01

P.O. Box 3093
3760 DB Soest
The Netherlands
Tel: 31 35 60 29 700
Fax: 31 35 60 29 214

Japan

Saint-Gobain KK, Crystals Division
3-7, Kojimachi, Chiyoda-ku,
Tokyo 102-0083 Japan
Tel: 81 (0) 3 3263 0559
Fax: 81 (0) 3 5212 2196


China

Saint-Gobain (China) Investment Co., Ltd.
15-01 CITIC Building
19 Jianguomenwai Ave.
Beijing 100004 China
Tel: 86 (0) 10 6513 0311
Fax: 86 (0) 10 6512 9843

www.detectors.saint-gobain.com

BC-414 Premium Plastic Scintillator

Emission Spectrum—



Manufacturer reserves the right to alter specifications.
©2005-8 Saint-Gobain Ceramics & Plastics, Inc. All rights reserved.

(07-08)