

BC-428

Green-Emitting Plastic Scintillator

BC-428 is a clear, transparent plastic scintillator with a bright green fluorescence. It is intended for use with photodiodes and charged coupled devices (CCDs) which have optical sensitivities in the green and red portions of the spectrum. Phoswich detectors and other special systems which use optical techniques advantageously for background reduction and selected signal enhancement also may employ BC-428.

Comparing BC-428 to BC-400 scintillator shows that BC-428 has about the same scintillation efficiency. However, its relative light output is 56% of BC-400's with bialkali photocathode PMTs and 85% with S-11 PMTs.

Scintillation Properties –

Light Output, %Anthracene	36
Rise Time (10-90%), ns	1.6
Integral Rise Time (10-90%), ns	30
Decay Time (1/e), ns	12.5
Wavelength of Maximum Emission, nm	480
Light Attenuation Length, 10 mm sheet, cm	150

Atomic Composition –

No. of H Atoms per cc	5.23×10^{22}
No. of C Atoms per cc	4.74×10^{22}
Ratio H:C Atoms	1.103
No. of Electrons per cc	3.37×10^{23}

General Technical Data –

Base	Polyvinyltoluene
Density	1.032 g/cc
Refractive Index	1.58
Coefficient of Linear Expansion	7.8×10^{-5} below 67°C
Light Output Temperature Dependence	at +60°C = 95% of that at +20°C; independent of temperature from -60°C to +20°C
Vapor Pressure	May be used in a vacuum
Solubility	Soluble in aromatic solvents, chlorine, acetone, etc. Insoluble in water, dilute acids, lower alcohols, silicone fluid, grease and alkalis.
Softening Point	70°C

Scintillation Products
Organic Scintillators



USA

Saint-Gobain Crystals
17900 Great Lakes Parkway
Hiram, OH 44234
Tel: (440) 834-5600
Fax: (440) 834-7680

Europe

Saint-Gobain Crystals
104 Route de Larchant
BP 521
77794 Nemours Cedex, France
Tel: 33 (1) 64 45 10 10
Fax: 33 (1) 64 45 10 01

P.O. Box 3093
3760 DB Soest
The Netherlands
Tel: 31 35 60 29 700
Fax: 31 35 60 29 214

Japan

Saint-Gobain KK, Crystals Division
3-7, Kojimachi, Chiyoda-ku,
Tokyo 102-0083 Japan
Tel: 81 (0) 3 3263 0559
Fax: 81 (0) 3 5212 2196


China

Saint-Gobain (China) Investment Co., Ltd.
15-01 CITIC Building
19 Jianguomenwai Ave.
Beijing 100004 China
Tel: 86 (0) 10 6513 0311
Fax: 86 (0) 10 6512 9843

www.detectors.saint-gobain.com

BC-428 Green-Emitting Plastic Scintillator

Emission Spectrum –



Manufacturer reserves the right to alter specifications.
©2005-8 Saint-Gobain Ceramics & Plastics, Inc. All rights reserved.

(07-08)