

# BC-444

## Long Timing Constant Plastic Scintillator

BC-444 is a plastic scintillator developed to have long timing properties. Applications include heavy ion research, particle identification, low background counting, active shielding and dosimetry. BC-444 can be used either by itself or in conjunction with a fast scintillator such as BC-400.

BC-444 is available in a variety of shapes and sizes. The material has the same kind of mechanical handling properties as Saint-Gobain Crystals other premium plastic scintillators.

### Scintillation Properties

Light Output, %Anthracene	41
Rise Time	19.5 ns
Decay Time	285 ns
Pulse Width, FWHM, ns	171.9
Wavelength of Maximum Emission, nm	428
Bulk Light Attenuation Length, cm	180

### Atomic Composition

No. of H Atoms per cc	$5.25 \times 10^{22}$
No. of C Atoms per cc	$4.73 \times 10^{22}$
Ratio H:C Atoms	1.109
No. of Electrons per cc	$3.37 \times 10^{22}$

### General Technical Data

Base	Polyvinyltoluene
Density	1.032 g/cc
Refractive Index	1.58 (n <sub>D</sub> ), 1.607 at wavelength of maximum emission
Coefficient of Linear Expansion	$\sim 7.8 \times 10^{-5}$ below 65°C
Vapor Pressure	May be used in a vacuum
Solubility	Soluble in aromatic solvents, chlorinated solvents, acetone, etc. It is unaffected by water, dilute acids, lower alcohols, alkalis, and pure silicone fluids or grease.
Softening Point	70°C

Scintillation Products



**USA**

**Saint-Gobain Crystals**  
17900 Great Lakes Parkway  
Hiram, OH 44234  
Tel: (440) 834-5600  
Fax: (440) 834-7680

**Europe**

**Saint-Gobain Crystals**  
104 Route de Larchant  
BP 521  
77794 Nemours Cedex, France  
Tel: 33 (1) 64 45 10 10  
Fax: 33 (1) 64 45 10 01

P.O. Box 3093  
3760 DB Soest  
The Netherlands  
Tel: 31 35 60 29 700  
Fax: 31 35 60 29 214

**Japan**

**Saint-Gobain KK, Crystals Division**  
3-7, Kojimachi, Chiyoda-ku,  
Tokyo 102-0083 Japan  
Tel: 81 (0) 3 3263 0559  
Fax: 81 (0) 3 5212 2196

**China**

**Saint-Gobain (China) Investment Co., Ltd**  
15-01 CITIC Building  
19 Jianguomenwai Ave.  
Beijing 100004 China  
Tel: 86 (0) 10 6513 0311  
Fax: 86 (0) 10 6512 9843


**India**

**Saint Gobain Crystals and Detectors Ltd**  
India Delegation , Leela Business Park  
Andheri Kurla Road  
Mumbai 400059 India  
Tel: 91 22 4021 2121  
Fax: 91 22 4021 2102

[www.detectors.saint-gobain.com](http://www.detectors.saint-gobain.com)

## BC-444 Long Timing Constant Plastic Scintillator

Emission Spectrum –



Manufacturer reserves the right to alter specifications.

©2005-12 Saint-Gobain Ceramics & Plastics, Inc. All rights reserved.

(05-12)